



Stikko MixoPlast

Ready Dry-Mix Plaster Mortar

<p>Product Description</p>	<p>Stikko MixoPlast is a premixed mortar with high quality polymer additives that makes application simple and convenient. It can be used on inner and outer walls made of brick, block, stone as well as concrete. It provides an even surface on which tiling can be done faster and efficiently. Pre-wetting of the substrate is essential.</p>																		
<p>Features</p>	<ul style="list-style-type: none"> <input type="checkbox"/> Used in place of traditional plastering <input type="checkbox"/> Consistent quality made by right composition of raw materials <input type="checkbox"/> Needs lesser curing, and binds better to its base <input type="checkbox"/> Prepared with a mix of special binders and additives, STIKKO MixoPlast is water resistant 																		
<p>Benefits</p>	<ul style="list-style-type: none"> <input type="checkbox"/> Uniform and smooth finish to walls <input type="checkbox"/> Quality plastering since it does not contain any impurity <input type="checkbox"/> Convenient to apply <input type="checkbox"/> Faster completion of work <input type="checkbox"/> Negligible wastage due to least rebound 																		
<p>Things to Remember</p>	<p>Curing should be done 2 – 3 times for 2 – 3 days in normal conditions.</p>																		
<p>Technical information (under normal test conditions)</p>	<table border="1"> <thead> <tr> <th>Sr.No.</th> <th>Properties</th> <th>Values</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>Bulk density</td> <td>1.2 - 1.6 kg/litre unit</td> </tr> <tr> <td>2</td> <td>Compressive strength (MPa)</td> <td>More than 4 in 28 days</td> </tr> <tr> <td>3</td> <td>Coverage</td> <td>1.7 - 2.4 kg/sq m/mm</td> </tr> <tr> <td>4</td> <td>Pot life</td> <td>2 hours</td> </tr> <tr> <td></td> <td>Water requirement</td> <td>17% to 19% by weight</td> </tr> </tbody> </table>	Sr.No.	Properties	Values	1	Bulk density	1.2 - 1.6 kg/litre unit	2	Compressive strength (MPa)	More than 4 in 28 days	3	Coverage	1.7 - 2.4 kg/sq m/mm	4	Pot life	2 hours		Water requirement	17% to 19% by weight
Sr.No.	Properties	Values																	
1	Bulk density	1.2 - 1.6 kg/litre unit																	
2	Compressive strength (MPa)	More than 4 in 28 days																	
3	Coverage	1.7 - 2.4 kg/sq m/mm																	
4	Pot life	2 hours																	
	Water requirement	17% to 19% by weight																	
<p>Packaging</p>	<p>Available in 40 kg PP laminated bags</p>																		