



## Stikko Repair Mortar 45

Ready To use Polymer modified Fibre Reinforced cementitious repair mortar

<b>Product Description</b>	Stikko repair mortar 45 ready to use blend of dry powders and fibres which requires only the addition of clean water to produce a highly consistent repair mortar suitable for most structural and load bearing repairs.
<b>Uses</b>	Used for wet spraying and hand application in a wide variety of repair applications and is particularly well suited to vertical and overhead repairs.
<b>advantages</b>	<ul style="list-style-type: none"> <li>&gt; Ready to use, only water to be added.</li> <li>&gt; specifically developed to provide an easy to apply product , suitable for local conditions</li> <li>&gt; alings performance closer than ever before , to that of host concrete</li> <li>&gt; positive benifits are easily demonstrated via a single, simple measurement</li> <li>&gt; Self curing</li> </ul>
<b>Product Data &amp; Technical information</b>	
Appearance/Colour	Grey
Packaging	30 Kg Bags
Mix Ratio	5.to 5.5 litres of 30 kg bag
Open Time	Approx 5-15 minutes @ 27+/-2 C.
Adjust - ability	5 mins (minimum) @ 27+/-2 C.
Minimum Applied Thickness	40 mm
Setting time	24 Hours
flexural Strength(28 days)	7 N/mm <sup>2</sup>
Tensile Adhesion (28 days)	2.5 N/mm <sup>2</sup>
Compressive Strength (28 Days)	45 mpa